



PVC/ABS Alloy SYNOLAC (Modified PVC/ABS)

Property	STANDARD ASTM	Unit	HI M-40	Super HI M-200	HF M-300	Medium HF M-1400	AA1701 Super HF M-3000
Flow Melt Flow Index @ 200 °C & 10 Kg load	D1238	gms/10 min	0.2 - 0.5	2 - 2.5	3 - 5	12- 20	24 - 30
Mechanical Tensile Strength @ Yield 50 mm/min	D638	MPa	35- 45	30 - 40	45 -65	40 - 60	42 -48
Tensile Elongation @ Yield	D638	%	8.5 - 9.5	9-10.5	8.5 -10	9 -10.5	8 - 10
Flexural Strength 5 mm/min	D790	MPa	55-60	40 - 50	50 -65	55 -70	52 - 55
Izod Notched Impact Strength	D256	J/m	350 -600	700-1000	200 -350	250 -400	425 - 450
Thermal Heat Deflection Temperature Under Load (B)1.82MPa	D 648	°C	50 -70	50 -70	50 -70	50 -70	58 - 62
Vicat Softening Temperature (B)	D 1525	°C	70 -90	70 -90	70 -90	70 -90	80 - 84
Other Density	D 792	gms/cc	1.20- 1.25	1.20- 1.25	1.20- 1.25	1.20- 1.25	1.24 - 1.25
Mould Shrinkage	D 955	%	0.2-0.5	0.2-0.5	0.2-0.5	0.2-0.5	0.2 - 0.5
Flammability Test @ 3mm thickness	UL 94		V0	V0	V0	V0	V0
Filler Content	D 5630	%	-	-	-	-	-

* Typical values represent an average for the samples tested using standard procedures.

The data indicated are intended as guides and do not reflect product specifications for any particular property

All information, direction or advice given by Gujarat Petrosynthese Ltd (GPL) as to the performance, characteristic, application, design or use of these material is given in good faith and the best of its knowledge. However, as GPL has no control over the use to which others put these materials, it does not accept any responsibility or any liability therefrom in connection with any services rendered by it or for the design, characteristic, performance of the materials either towards any purchaser or user thereof or towards any third party. Each user of these materials should make his own tests to determine the material's suitability for his own particular use. GPL or any of their subsidiary companies or distributors can not be held responsible for any loses incurred by incorrect use of material. In accordance with the policy of these companies of continuous product development , users are advised to check the most up to date information.



GUJARAT PETROSYNTHESE LIMITED

Polymer Alloys & Blends Division

No.24, II Main, Phase I, Doddanekkundi Indl. Area
Mahadevapura Post, Behind Graphite India Ltd., Bangalore-560048
Phone : 91-080-28524133 Fax : 91-080-28524171 E-mail : info@gpl.in

Agents: