
	ALLOYS & BLENDS												
	SYNONATE(PC/ABS)												
Properties	STANDAR D ASTM	Unit	CA4701	M810 CB4701 /M800 I	CA1706 FR GF 30	CA4706 GF 30	CB1702 FR V0 GF 10	CA1701 FR V0	CA2701 FR V1	CB2601 FR V1	CA4702 GF10	CB3701 FR V2	CB1701 FRV0
Flow													
Melt Flow Index @ 260C & 2.16 Kg load	D1238	gms/10 min	4 - 7	4 - 7	12 - 17	10 -15	9 - 12	4 - 8	4 - 6	3 - 8	7 - 12	20 - 25	4 - 8
Mechanical													
Tensile Strength @ Yield 50 mm/min	D638	MPa	44 - 49	44-49	60 - 80	65 - 85	55 -60	43-49	45 -50	42 - 55	55 -68	50 - 54	43-49
Tensile Elongation @ Yield	D638	%	7 - 11	7 - 11	5 - 10	3 - 8	6 - 9	7 - 11	6 - 9	9 - 13	6 - 10	8 - 10	7 - 11
Flexural Strength 5 mm/min	D790	MPa	70 - 90	70 - 90	90 - 120	95-125	83 - 87	60 -75	60 -70	65-90	86- 100	--	--
Flexural Modulus	D790	MPa	2200 -3200	2200 -3200	6000-7500	6500-8500	4100 - 4600	2100 - 3200	2100 - 3200	2200 - 3200	4100-5200	--	--
Izod Notched Impact Strength	D256	J/m	500-700**	450 - 600	60 - 80	70 - 90	125- 150	450-550	350-650	400- 700	120-150	228 - 238	700-850**
Thermal													
Heat Deflection Temperature Under Load (B)1.82MPa	D 648	C	95-105	95 - 105	120 -150	120 -150	130- 136	105-115	95 - 110	100- 105	130- 142	112 - 118	105-115
Vicat Softening Temperature (B)	D 1525	C	130 - 135	130 - 135	-	-	154- 160	120-140	120-140	130- 135	-	--	--
Others													
Density	D 792	gms/cc	1.10-1.14	1.10-1.14	1.39-1.45	1.39-1.42	1.15-1.22	1.15-1.17	1.15-1.24	1.10-1.14	1.15-1.22	1.11 - 1.14	1.15-1.17
Flammability Test @ 3mm thickness	UL 94		-----	----	V0	-	V0	V0	V1	V1	-	V2	V0
Filler Content	D 5630	%	-	-	28 - 32	28 - 32	9 -11	-	-	-	8 - 12	-	--

* Typical values represent an average for the samples tested using standard procedures. **Impact Strength @ 3.2 mm thickness, all other properties @ 6.4mm thickness

The data indicated are intended as guides and do not reflect product specifications for any particular property

All information, direction or advice given by Gujarat Petrosynthese Ltd (GPL) as to the performance, characteristic, application, design or use of these material is given in good faith and the best of its knowledge. However, as GPL has no control over the use to which others put these materials, it does not accept any responsibility or any liability therefrom in connection with any services rendered by it or for the design, characteristic, performance of the materials either towards any purchaser or user thereof or towards any third party. Each user of these materials should make his own tests to determine the material's suitability for his own particular use. GPL or any of their subsidiary companies or distributors can not be held responsible for any loses incurred by incorrect use of material. In accordance with the policy of these companies of continuous product development , users are advised to check the most up to date information.


		GUJARAT PETROSYNTHESE LIMITED	
Polymer Alloys & Blends Division		Agents:	
No.24, II Main, Phase I, Doddanekkundi Indl. Area			
Mahadevapura Post, Behind Graphite India Ltd., Bangalore-560048			
Phone : 91-080-28524133 Fax : 91-080-28524171. E-mail : inf@gpl.in			

	ALLOYS & BLENDS SYNONATE(PC/ABS)												
Properties	STANDAR D ASTM	Unit	CC1701 Hi-Flow FR V0										
Flow													
Melt Flow Index @ 260C & 2.16 Kg load	D1238	gms/10 min	15-20										
Mechanical													
Tensile Strength @ Yield 50 mm/min	D638	MPa	57-65										
Tensile Elongation @ Yield	D638	%	7 – 10										
Flexural Strength 5 mm/min	D790	MPa	--										
Flexural Modulus	D790	MPa	70-100										
Izod Notched Impact Strength	D256	J/m	250-350**										
Thermal													
Heat Deflection Temperature Under Load (B)1.82MPa	D 648	C	90-100										
Vicat Softening Temperature (B)	D 1525	C	--										
Others													
Density	D 792	gms/cc	1.12 – 1.16										
Flammability Test @ 3mm thickness	UL 94		V0										
Filler Content	D 5630	%	NA										

* Typical values represent an average for the samples tested using standard procedures. **Impact Strength @ 3.2 mm thickness, all other properties @ 6.4mm thickness

The data indicated are intended as guides and do not reflect product specifications for any particular property

All information, direction or advice given by Gujarat Petrosynthese Ltd (GPL) as to the performance, characteristic, application, design or use of these material is given in good faith and the best of its knowledge. However, as GPL has no control over the use to which others put these materials, it does not accept any responsibility or any liability therefrom in connection with any services rendered by it or for the design, characteristic, performance of the materials either towards any purchaser or user thereof or towards any third party. Each user of these materials should make his own tests to determine the material's suitability for his own particular use. GPL or any of their subsidiary companies or distributors can not be held responsible for any losses incurred by incorrect use of material. In accordance with the policy of these companies of continuous product development, users are advised to check the most up to date information.

		GUJARAT PETROSYNTHESE LIMITED	
Polymer Alloys & Blends Division No.24, II Main, Phase I, Doddanekkundi Indl. Area Mahadevapura Post, Behind Graphite India Ltd., Bangalore-560048 Phone : 91-080-28524133 Fax : 91-080-28524171. E-mail : inf@gpl.in		Agents:	