

	<b>SYNONATE (Modified PC)</b>												
Properties	STANDAR D ASTM	Unit	MA4601/ 4701 General (Coloured)	Speciality Grades									
				MA1601/MA 1701 FR	MA1601 FR UV	MA1602/ 1702 FR GF10	MA1704 FR GF20	MA4704 GF20	MA4706 GF30				
<b>Flow</b>													
Melt Flow Index @ 300C & 1.2 Kg load	D1238	gms/10 min	10-15	10-16	10-16	15 - 20	16-22	12-18	16 - 30				
<b>Mechanical</b>													
Tensile Strength @ Yield 50 mm/min	D638	MPa	54 - 64	50 - 65	54 - 64	60 - 72	64-75	60-70	75 - 120				
Tensile Elongation @ Yield	D638	%	9-15	9-15	9-15	8-14	8-12	8-12	8-12				
Flexural Strength 5 mm/min	D790	MPa	80 - 94	80 - 90	80 - 98	95 - 105	100-110	100-110	128 - 150				
Flexural Modulus	D790	MPa	2200-3200	2200-3200	2000-3200	3000-4500	3200-5000	3500-5500	5700-7000				
Izod Notched Impact Strength	D256	J/m	800 - 1100**	700 - 900**	400 - 700	90 - 150	95-150	110-170	90 - 150				
<b>Thermal</b>													
Heat Deflection Temperature Under	D 648	C	128 - 134	120 - 134	128 - 134	132 - 138	135-140	135-140	138 - 145				
Vicat Softening Temperature (B)	D 1525	C	150 - 158	150 - 158	150 - 158	154 - 158	155-160	155-160	155 - 165				
<b>Others</b> Density	D 792	gms/cc	1.19 - 1.22	1.20 - 1.35	1.20 - 1.25	1.25- 1.32	1.27-1.36	1.25-1.35	1.34 - 1.40				
Flammability Test @ 3mm thickness	UL 94		V2	V0	V0	V0	V0	V2	V2				
Filler Content	D 5630	%	-	-	-	9-11	19 - 21	19 - 21	29 - 31				

\* Typical values represent an average for the samples tested using standard procedures.

\*\*Impact Strength @ 3.2 mm thickness, all other properties @ 6.4mm thickness

The data indicated are intended as guides and do not reflect product specifications for any particular property

All information, direction or advice given by Gujarat Petrosynthese Ltd (GPL) as to the performance, characteristic, application, design or use of these material is given in good faith and the best of its knowledge. However, as GPL has no control over the use to which others put these materials, it does not accept any responsibility or any liability therefrom in connection with any services rendered by it or for the design, characteristic, performance of the materials either towards any purchaser or user thereof or towards any third party. Each user of these materials should make his own tests to determine the material's suitability for his own particular use. GPL or any of their subsidiary companies or distributors can not be held responsible for any losses incurred by incorrect use of material. In accordance with the policy of these companies of continuous product development, users are advised to check the most up to date information.

<div data-bbox="378 1214 497 1263"></div> <div data-bbox="743 1247 1251 1276" style="text-align: center;"><b>GUJARAT PETROSYNTHESE LIMITED</b></div> <div data-bbox="58 1286 1108 1440"> <b>Polymer Alloys &amp; Blends Division</b>  <b>No.24, II Main, Phase I, Doddanekkundi Indl. Area</b>  <b>Mahadevapura Post, Behind Graphite India Ltd., Bangalore-560048</b>  <b>Phone : 91-080-28524133 Fax : 91-080-28524171. E-mail : info@gpl.in</b> </div>		<b>Agents:</b>
--	--	----------------